



PO Box 16017
Hornby
Christchurch 8441

Phone: 03 344 0260

Fax: 03 3498732

info@agrippapaints.co.nz
www.agrippapaints.co.nz



TIMBERSTYLE

Deck & Timber Paint

PRODUCT INFORMATION

DESCRIPTION: A premium, tough, water based, low VOC, 100% acrylic low sheen finish for exterior timber, concrete and fibre cement surfaces.

PROPERTIES: TIMBERSTYLE 100% acrylic polymer provides exceptional protection from the sun and weather without the need for a primer or undercoat.
TIMBERSTYLE is a fast-drying paint that can be applied on substrates at temperatures as low as 5°C. TIMBERSTYLE provides outstanding weather protection drying to a low sheen finish with high opacity, excellent UV resistance and weatherability.

PRINCIPAL USES: TIMBERSTYLE can be used as a finish coat, undercoat and primer on most exterior surfaces.
Typical areas of use are Timber Decks, Weatherboards, Fences, Trelliswork, Fibre-Cement surfaces, Concrete Blocks and Unglazed Bricks.

LIMITATIONS: Please refer to "Preparation" before use.
On unusual or nonstandard surfaces, you should test this product to determine if it is suitable for your particular use. Some precoated or pre-primed substrates may require re-priming prior to application of TIMBERSTYLE. Please refer to the manufacturer of the substrate for their recommendations.
Do not apply when temperature is below 5°C, or rainfall is likely within 24 hours of application.

COLOURS: Tasman Black, Dixon Grey, Hicks Grey, Torres Rustic Tan, Sefton Red, Douglas Brown, Haast Green, White
Note: Always colour test first to check your choice of TIMBERSTYLE colour gives the result you want on the surface you are painting.

APPLICATION DATA:

Surface Preparation:

All surfaces:

Remove any old flaking paint by scraping or water blasting. Ensure the surface is sound, clean and free of mould and moss, dirt, oil, grease, bird droppings or other contaminants.

Mould, Moss & Lichen:

If mould, moss or lichen is present, pre-treat the surfaces in advance with NOVEX TREAT-IT Fungicidal Treatment & Cleaner and leave for at least 2 weeks, then remove dead material and dirt by scraping, scrubbing or water blasting. Leave to dry.

Note: Removal of these is critical to achieving a successful long-term decorative PAINT system and to achieve this you need to treat, leave until it has died then remove.

New Decks:

New pine decking timber should be weathered for 8 weeks.

Hardwood decks should be weathered for 12 weeks. Clean and treat with NOVEX TIMBER CLEAN & PREP before the application of TIMBERSTYLE Deck & Timber Paint - this also opens the fibres to aid penetration. Apply two full coats of TIMBERSTYLE.

Note: Shiny (mill glazed) machined timber surfaces should be sanded to allow penetration.

Weathered Decks - incl Previously Stained & Oiled

Clean and treat with NOVEX TIMBER CLEAN & PREP before the application of TIMBERSTYLE Deck & Timber Paint - this also opens the fibres to aid penetration. Heavily oiled surfaces may require sanding back to a clean sound surface. Apply two full coats of TIMBERSTYLE.

Date Issued: January 2025

Page 1 of 2

The information concerning the use and application of our products is supplied in good faith, based on our experience and tests. However, subject to our standard Terms & Conditions of Sale (available on request) and any implied terms, conditions, or warranties imposed by the Consumer Guarantees Act 1993 the recommendations and suggestions herein are made without guarantee, as application conditions are out of our control. Adequate tests should be made to ensure product or recommendations suitability. We reserve the right to alter product or specification without notice.

"There shall be no right of redress against the manufacturer under the Consumer Guarantees Act 1993 in respect of goods which fail to comply with any express guarantees made by the manufacturer in relation to the information contained herein where the goods have failed for reasons beyond the control of the manufacturer".

Application details are based on generic scenarios, for any specific application not mentioned above, details please contact Agrippa Paints directly.

This product would be expected to be fit for purpose and perform as stated in this data sheet, provided the substrate is in good condition and preparation and application is completed as recommended to a high standard and application is carried out by a suitably skilled/experienced applicator.

The user should check the date of issue, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current.

Timber Surfaces:

If timber surfaces (inc fences) have been water blasted, please check to ensure excessive loose wood fibres are not present (as high pressure washing often leaves a 'fluffy' surface on timber). If excessive loose fibres are present or you have a weathered, absorbent timber surface, we recommend applying an initial primer coat of TIMBERSTYLE thinned 10% with water, followed by two full finish coats.

Note: Heavy water blasting is not recommended on timber surfaces as it can "fluff" the timber surface, use a low-medium pressure wash down and/or scrubbing.

Previously Painted Surfaces:

Remove any flaking paint using a scraper, wire brush and/or sand as necessary.
Glossy surfaces must be sanded to a dull finish with 200 grit sandpaper before repainting.
Fill holes and cracks with a suitable filler. Sand the surface smooth with 150 or 180 grit sandpaper.
When painting over an unknown coating or when changing products, apply to a small area to check compatibility.
Note: All sanding dusts can be harmful. When sanding any surface wear an appropriate dust mask. Avoid breathing the dust.

Concrete Surfaces:

Ensure any fresh concrete is allowed to cure at least 28 days prior to painting.
Smooth bare concrete or if the surface is steel trowelled or any laitance is present the concrete will need to be etched with NOVEX AP Prep Etch Concrete Etch prior to painting. The Acid etched needs to produce a roughen the surface (as rough as 100 grit sandpaper).

If the surface does not have an appearance like 100 grit sandpaper, a second application may be required in certain areas. Allow 3-4 days to dry thoroughly before painting. The floor may be professionally ground if acid etching is not possible. If the surface is porous or has been ground, a 10% thinned coat of TIMBERSTYLE as a primer is required, followed by two full finish coats.

Concrete or Clay Tiles & Unglazed Brick:

Old or weathered tiles and brick may have an unsound surface. Check the tiles or unglazed brick after cleaning and preparation with adhesive tape. If significant grit is removed from their surface with the adhesive tape, a coat of Easy Seal Solvent Roof Glaze must be applied prior to application of TIMBERSTYLE. Apply two coats of TIMBERSTYLE.

Application:

Apply on a fine day. Avoid application if humidity is greater than 85%, dew or rainfall is likely within 4 hours, or the temperature is below 5°C.
Stir well before use, with a wide flat stirrer in a circulating "bottom to top" motion.
Apply with a good quality brush, roller or airless spray.
Two full finish coats are recommended to give greater durability and protection to the surface.
To aid adhesion and to seal new, porous, weathered surfaces, a 10% water thinned coat of TIMBERSTYLE as a primer is required followed by two full finish coats.

Note: If the project requires more than one pail of product (especially different batches) it is good practice to add some of the new pail to the last of the old pail during application to ensure colour uniformity.

Drying Time & Recoat:

As a guide, TIMBERSTYLE will be touch dry in approximately 30 minutes and can be recoated after 2 hours. Leave to dry overnight before walking on the finished surface.
Note: Drying and curing times will vary depending on temperature and humidity conditions at time of application.

Clean-up:

Wash equipment with cold water.
Protect our Environment – When disposing of leftover liquid, keep out of stormwater drains and waterways. Take to a local hazardous waste disposal station. Dry all empty containers in a well-ventilated area. Dispose of the empty containers according to your local council regulations.

Maintenance:

We recommend washing every 12 months (after each winter is a great time) with NOVEX TREAT-IT Fungicidal Treatment & Cleaner to remove dirt deposits. Dirt, salt and bird deposits left on the surface will encourage the growth of mould and negatively affect the paints performance.

GENERAL DATA

Gloss Level: Low Sheen.

Theoretical Coverage: 8-16 square metres per litre per coat depending on the texture and profile.

Application Conditions: Do not apply when temperature is below 5°C, the humidity is greater than 85% or if dew or rainfall is likely within 4 hours of application.

Shelf Life: Store in cool conditions, away from direct sunlight. Under normal conditions full containers can be stored for several years. Check contents before use.

Specific Gravity: Approximately 1.20 (varies slightly with colour) = 1.20 kg/litre.

Sizes Available: TIMBERSTYLE is supplied in test pots, 4 Litres, 10 Litres plastic containers.

Low VOC:

What does "Low VOC" mean? Low VOC paints have a reduced amount of volatile organic compounds. Therefore, the paint won't give off as many fumes, compared to traditional paints. This translates into a more pleasant painting experience.