



AGRIPPA PAINTS LTD

PO Box 16017
Hornby
Christchurch 8441

Phone: 03 344 0260

Fax: 03 3498732

info@agrippapaints.co.nz
www.agrippapaints.co.nz



AP PREP ETCH

Concrete Etch

PRODUCT INFORMATION

DESCRIPTION:

AP PREP ETCH is a low odour, environmentally friendly safe etch for use on concrete surfaces to obtain a surface profile for optimum adhesion. This is done by chemically reacting with surface laitance to give a slightly etched finish to the surface. A safer alternative to hydrochloric acid etches. Safe near plants and grass.

PROPERTIES:

AP PREP ETCH is supplied as a concentrated powder which is dissolved in water to provide a solution that roughens concrete.

PRINCIPAL USES:

AP PREP ETCH is used on concrete floors, driveways, garage floors, steps and all concrete drive-on and walk-on surfaces to ensure a surface profile that provides maximum adhesion of appropriate finishing systems. Can also be used to reduce the effects of efflorescence salts. There is no benefit for use on previously coated floors.

APPLICATION DATA:

Surface Preparation:

Allow 28 days for freshly laid concrete to cure prior to the application of AP PREP ETCH. Before applying AP PREP ETCH, sweep the concrete surface to remove any loose or powdery material. Any oil contamination on unpainted concrete floors should be removed with a proprietary degreaser or oil remover before using AP PREP ETCH.

Application:

Add 1 kg of AP PREP ETCH to 5 litres of water and mix thoroughly until the AP PREP ETCH is dissolved.

5 litres is sufficient to treat approximately 20 m² of bare concrete.

Apply AP PREP ETCH solution to the concrete using a plastic watering can at a rate of 4 m²/litre. Bubbling should be evident over the entire surface. If there is no bubbling evident, clean the surface with a suitable detergent and repeat the application of AP PREP ETCH solution. Ensure the surface is "kept wet" during the etching process by sprinkling water to any areas that start to dry. A damp floor acts as a buffer to assist with preventing an uneven etch.

Once bubbling has begun to subside (5-15 min), scrub the surface with a stiff nylon broom then rinse off with copious amounts of clean water whilst at the same time scrubbing with a stiff broom to remove the loose concrete salts and most importantly neutralise the acid. Use of a mild alkaline detergent to clean the surface once bubbling has subsided is also suggested to assist with neutralising of the acid.

It is important to ensure no residual acid remains on the concrete surface. If this is not done correctly paint adhesion failure may occur.

Touch Dry:

Not Applicable.

Recoat:

Maybe required to be repeated if desired etch profile of a medium grit sandpaper has not been achieved.

Clean-up:

Clean and wash up with water.

Protect Our Environment – AP PREP ETCH is a natural product that presents no significant hazard to the environment. Any unwanted solution can be flushed away with running water. Avoid discharge into stormwater drains, sewers and waterways. Dispose of the empty containers according to your local council regulations.

GENERAL DATA

Gloss Level:

Not Applicable.

Theoretical Coverage:

The made-up solution of AP PREP ETCH should be applied at the rate of 4 m² per litre.

Application Temperature:

Not Applicable.

Shelf Life:

Store in cool conditions, away from direct sunlight. Under normal conditions full containers can be stored for several years. Check contents before use.

Specific Gravity:

Not Applicable.

Sizes Available:

1kg plastic container.

Date Issued: February 2025

Page 1 of 1

The information concerning the use and application of our products is supplied in good faith, based on our experience and tests. However, subject to our standard Terms & Conditions of Sale (available on request) and any implied terms, conditions, or warranties imposed by the Consumer Guarantees Act 1993 the recommendations and suggestions herein are made without guarantee, as application conditions are out of our control. Adequate tests should be made to ensure product or recommendations suitability. We reserve the right to alter product or specification without notice.

"There shall be no right of redress against the manufacturer under the Consumer Guarantees Act 1993 in respect of goods which fail to comply with any express guarantees made by the manufacturer in relation to the information contained herein where the goods have failed for reasons beyond the control of the manufacturer".

Application details are based on generic scenarios, for any specific application not mentioned above, details please contact Agrippa Paints directly.

This product would be expected to be fit for purpose and perform as stated in this data sheet, provided the substrate is in good condition and preparation and application is completed as recommended to a high standard and application is carried out by a suitably skilled/experienced applicator.

The user should check the date of issue, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current.