



PO Box 16017  
Hornby  
Christchurch 8441

Phone: 03 344 0260

Fax: 03 3498732

info@agrippapaints.co.nz  
www.agrippapaints.co.nz



# ENZAC

## Acrylic Enamel

### PRODUCT INFORMATION

**DESCRIPTION:** ENZAC Acrylic Enamel is an advanced formulation hard wearing acrylic enamel in a semi gloss finish, ideal for areas traditionally finished with solvent-based enamels.

**PROPERTIES:** ENZAC Acrylic Enamel has the smooth finishing properties and serviceability of enamels with the non-yellowing, low VOC, quick dry, water washup and convenience characteristics of water-based finishes. ENZAC Acrylic Enamel is suitable for both interior and exterior applications. ENZAC Acrylic Enamel is a fast-drying paint that can be applied on substrates at temperatures as low as 5°C.

**PRINCIPAL USES:** ENZAC Acrylic Enamel has been formulated specifically to be able to provide outstanding wear on windows, doors and trim throughout the home. ENZAC Acrylic Enamel also be used on the walls of interior service areas such as kitchens, laundries and bathrooms. The non-blocking properties of ENZAC Acrylic Enamel makes it ideal for use on timber windows and doors and their trim. Contact surfaces should be left for a minimum of 8 hours before closing.

**LIMITATIONS:** Please refer to "Preparation" before use. On unusual or non-standard surfaces, you should test this product to determine if it is suitable for your particular use. Do not apply when temperature is below 5°C.

**GUARANTEE:** Agrippa Paints guarantee that NOVEX ENZAC Acrylic Enamel Paint when used for exterior applications only, will not peel, blister or flake for 15 years provided it is maintained and applied correctly on sound and properly prepared surfaces as per the label and current technical data sheet instructions. This guarantee does not cover paint failure caused by any breakdown of coatings applied previously, incorrect use of the product or from mechanical damage. No warranty is offered for walk on surfaces. If this paint fails to perform as specified, Agrippa Paints will provide, free of charge, sufficient paint to recoat the affected areas. Proof of purchase is required.

**COLOURS:** A comprehensive range of colours tinted off White, Mid and Accent Bases are available.

### **APPLICATION DATA:**

#### **Surface Preparation:**

**All Surfaces:** Surfaces must be sound, clean, dry and free from dirt, oil, grease, mould, moss, soot, lichen, salt, bird droppings and other contaminants. All loose, peeling and flaking material must be removed. Glossy surfaces must be sanded to a dull finish with 200 grit sandpaper before repainting. Fill holes and cracks with a suitable filler. Sand the surface smooth with 150 or 180 grit sandpaper. Apply the appropriate sealer or undercoat to the substrate as outlined below and allow to dry before lightly sanding and overcoating with two coats of ENZAC Acrylic Enamel.  
**Interior:** If mould is present treat with a proprietary mould killer as per label directions. Remove grease by washing down with liquid sugar soap as per label directions.  
**Exterior:** If mould, moss or lichen is present treat with a proprietary moss and mould killer such as NOVEX TREAT-IT Fungicidal Treatment & Cleaner as per label directions.

**Note:** All sanding dust can be harmful. When sanding any surface wear an appropriate dust mask. Avoid breathing the dust.

**Bare Timber & MDF:** NOVEX COVERWELL Primer Sealer Undercoat, followed by 2 coats of ENZAC Acrylic Enamel.

**Pre-primed Timber & MDF:** Lightly sand and apply 2 coats of ENZAC Acrylic Enamel.

**Note:** If there is any doubt as to the condition of the primer, the timber has become wet prior to installation or the pre-primed timber has been exposed to weather for more than one month then the pre-primed timber should be re-primed with NOVEX Primer Sealer Undercoat.

**Fibre Cement:** NOVEX COVERWELL Primer Sealer Undercoat. Apply 2 coats of ENZAC Acrylic Enamel.

**Bare Paper Covered Plasterboard (Gib®):**  
NOVEX COVERWELL Pigmented Sealer Water Based, followed by 2 coats of ENZAC Acrylic Enamel.

**Sunburnt and Skim Coated Paper Covered Plasterboard (Gib®):**  
NOVEX COVERWELL Pigmented Sealer Oil Based, followed by 2 coats of ENZAC Acrylic Enamel.

**Wet area paper faced Plasterboard (Gib Aqualine®):**  
NOVEX COVERWELL Pigmented Sealer Oil Based, followed by 2 coats of ENZAC Acrylic Enamel.

**Previously Painted Surfaces:**  
Spot prime any bare areas after preparation as outlined above with NOVEX COVERWELL Primer Sealer Undercoat, followed by 2 coats of ENZAC Acrylic Enamel.

**Application:** Apply on a fine day. Avoid application if rain is forecast within 24 hours or the temperature is below 5°C. Stir well before use, with a wide flat stirrer in a circulating "bottom to top" motion. Apply with a good quality brush, 6-8mm nap roller or by airless spray. Two full finish coats are recommended to give greater durability and protection to the surface. Apply the paint evenly and generously. Spread fully with slow, even brush strokes before laying off in one direction. Do not overwork the finish.

**Note:** If the project requires more than one pail of product (especially tinted colours and different batches) it is good practice to finish off with one pail at a corner and then adding the last of the old pail to the new pail to ensure colour uniformity.

**Drying Time & Recoat:**  
As a guide, ENZAC Acrylic Enamel will be touch dry in approximately 30 minutes and can be recoated after 2 hours.

**Notes:** Drying and curing times will vary depending on temperature and humidity conditions at the time of application. To avoid blocking, contact surfaces should be left for a minimum of 8 hours before closing.

**Clean-up:** Wash equipment with cold water.

## GENERAL DATA

**Gloss Level:** Semi gloss

**Theoretical Coverage:**  
Allow 14-16 square metres per litre per coat depending on the texture and profile.

**Shelf Life:** Store in cool conditions, away from direct sunlight. Under normal conditions, full containers can be stored for several years. Check contents before use.

**Specific Gravity:** White - approximately 1.30 = 1.30 kg/litre.

**Sizes Available:** ENZAC Acrylic Enamel is supplied in 1 Litre & 4 Litre cans.

**Low VOC:** What does "Low VOC" mean? Low VOC paints have a reduced amount of volatile organic compounds. Therefore, the paint won't give off as many fumes, compared to traditional enamels. This translates into a more pleasant painting experience.

**Maintenance:** For exterior use, we recommend washing every 12 months (after each winter is a great time) with NOVEX TREAT-IT Fungicidal Treatment & Cleaner to remove dirt deposits. Dirt, salt and bird deposits left on the surface will encourage the growth of mould and negatively affect the paints performance.

## PROTECT OUR ENVIRONMENT

When disposing of leftover liquid, keep out of stormwater drains and waterways. Take to a local hazardous waste disposal station. Dry all empty containers in a well-ventilated area. Re-use or dispose of the empty containers according to your local council regulations.

The information concerning the use and application of our products is supplied in good faith, based on our experience and tests. However, subject to our standard Terms & Conditions of Sale (available on request) and any implied terms, conditions, or warranties imposed by the Consumer Guarantees Act 1993 the recommendations and suggestions herein are made without guarantee, as application conditions are out of our control. Adequate tests should be made to ensure product or recommendations suitability. We reserve the right to alter product or specification without notice.

"There shall be no right of redress against the manufacturer under the Consumer Guarantees Act 1993 in respect of goods which fail to comply with any express guarantees made by the manufacturer in relation to the information contained herein where the goods have failed for reasons beyond the control of the manufacturer".

Application details are based on generic scenarios, for any specific application not mentioned above, details please contact Agrippa Paints directly.

This product would be expected to be fit for purpose and perform as stated in this data sheet, provided the substrate is in good condition and preparation and application is completed as recommended to a high standard, and application is carried out by a suitably skilled/experienced applicator.

The user should check the date of issue, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current.